

SELA-TUBULAR

LMXT Range Low Maintenance
Tubular Batteries For Solar Application





EXIDE LMXT SERIES TUBULAR LEAD ACID BATTERIES FOR SOLAR PHOTOVOLTAIC APPLICATION

Exide Industries Ltd, the leader of Lead Acid battery manufacturers in India for more than 65 years is proud to present the new LMXT range of Tubular low maintenance lead acid batteries specially designed for SPV and other renewable energy based applications.

focus on renewable energy usage to meet the growing power demand of the country has increased manifold. It is considered to be the efficient solution to vast stretches of remote areas where mains power is yet to reach in an economic manner.

The success of SPV system largely depends on the efficiency of its storage. Storage of solar power is a challenge as the electricity produced from solar panels are intermittent and specially designed battery is required to effectively store this electricity and provide power optimally whenever required. The battery thus used is to be suitable to withstand daily charge-discharge cycle to work optimally in partial State of Charge (PSOC) situation with rapid recharging compatibility.

Exide's latest addition in Tubular series is the LMXT range of batteries specially designed and manufactured to suit the rigors of SPV application having the following unique features:

- Legendary Törr Tubular Positive Plates with specially selected alloys made in high pressure HADI casting machine which imparts longer life, ultra low topping up and high reliability
- Excellent Cycle life 1500 Cycles at 80% DOD & 7500 Cycles at 20% DOD Special type non woven gauntlet for positive plates results extra life of battery Batteries upto 800AH are fitted with MS modules (8/6/4V) so that the compact modules can be installed straightway on arrival at site (stands not required)
- Batteries are supplied in factory charged condition (unless otherwise specified by customer) and thus ready to install and use
- Easy to Handle & Transport
- · Conforms to IS 1651 specification with latest amendments



EXIDE LMXT SERIES: THE BEST VALUE FOR MONEY IN SPV APPLICATION.

Table:1

TECHNICAL CHARACTERISTICS

Model		Dimensions in mm				Weight (kg)			
	Nominal Voltage	C10 1.85 V/C	C20 1.85 V/C	Length ±5	Width ±5	Height ±5	Dry ± 5%	Filled ±5%	Re-charging Current (amps)
LMXT 400	2V	400	480	125	158	699	17	27	48
LMXT 500	2V	500	600	173//	158	699	23	38	60
LMXT 600	2V	600	720	173//	158	699	28	41	72
LMXT 700	2V	700	840	205	158	753	31	51	84
LMXT 800	2V	800	960	205	158	753	35	53	96
LMXT 900	2V	900	1080	416	171	535	44	70	108
LMXT 1000	2V	1000	1200	416	171	535	48	72	120

Table:2

		100						
Ì	Model	Nominal Voltage	Acid Qty (Ltrs)	Starting	Finishing	Minimum Ah Input during Initial Charging	Electrolyte Specific Gravity	
Ì	LMXT 300	2V	6	36	18	1650	Initial filling	
ĺ	LMXT 400	2V	8	48	24	2200		
ì	LMXT 500	2V	12	60	30	2750	gravity-1.220 ±0.005	
	LMXT 600	2V	11	72	36	3300	10.005	
	LMXT 700	2V	16	84	42	3850	Fully Charged	
	LMXT 800	2V	15	96	48	4400	Gravity-1.245	
ĺ	LMXT 900	2V	21	108	54	4950	±0.005	
ĺ	LMXT 1000	2V	20	120	60	5500		

Normally LMXT series batteries are supplied in Factory charged condition. In case of supply of batteries in Dry and Uncharged condition, the initial filling and charging at site is to be done as per the parameters given.

COMMISSIONING CHARGE OF BATTERY:

Before commissioning a new battery, follow procedure either procedure (a) or (b). However, procedure (a) is recommended.

a) I U method (bulk charge):

Bulk charging is performed at a raised voltage of 2.40 to 2.45 volts per cell. The charging time will be 12 to 24 hours depending on the state of charge condition during installations. The current is required to be limited to 20% of the battery Ah capacity (0.2 C10). The specific gravity of each cells rise to the maximum level (1.240 to 1.245) and remains constant till four consecutive hourly readings.

Bulk charging must be switched off or switched over to float charging as soon as the fully charged state is reached.

b) Float Charge:

With a voltage of 2.30 volt per cell.

Full capacity will however be obtained after a long period of 4 to 6 weeks (depending on state of charge) till three consecutively hourly readings of specific gravity are observed to constant.

After the above operation, re-check specific gravity of all cells and adjust to final specific gravity at 1.240 ± 0.005 by taking out electrolyte and adding DM water.

RECHARGING CHARACTERISTICS DURING OPERATIONS:

	Recommended Parameters for ambient temperature of 25-30°C					
Charging Current	Maximum - 20% of the battery Ah capacity Minimum - 10% of the battery Ah capacity					
Bulk Voltage	2.60 ± 0.02 V/cell					
Float Voltage	2.30 ± 0.02 V/cell					
Equalizing voltage	2.45 ± 0.02 V/cell					
Load Reconnect voltage	2.16 ± 0.02 V/cell					
Low Voltage disconnect	1.90 ± 0.02 V/cell					
Recharge factor	110% of discharge Ah					
Temperature Correction Factor (reference 25°C)	Float : - 3mV/°C/2V unit Cyclic : - 5mV/°C/2V unit					


Table:3 STANDARD LAYOUT OF BATTERY BANK IN SINGLE TIER ARRANGEMENT


Battery Type	Module Voltage & Module Dimensions	System Voltage	No. of Modules	No. of Rows	Dimensions (mm)		
					Length (±5)	Width (±5)	Height (±5)
LMXT300	8V	48V	6	2	3150	2064	554
	700(L) x 157(W) x 336(H)	96V	12	4	3150	3328	554
		120V	15	4	3900	3328	554
		240V	30	6	4650	4592	554
		360V	45	8	5400	5856	554
LMXT400	6V	48V	8	2	3308	2064	705
	552(L) x 157(W) x 448(H)	96V	16	2 4	3308	3328	705
		120V	20	4	3910	3328	705
		240V	40	6	6920	3328	705
		360V	60	6	6920	4592	705
LMXT500 & LMXT600	6V	48V	8	2	3308	2160	705
	552(L) x 205(W) x 445(H)	96V	16	4	3308	3520	705
		120V	20	4	3910	3520	705
		240V	40	6	5114	4880	705
		360V	60	6	6920	4880	705
LMXT700 & LMXT800	4V	48V	12	2	3522	2224	755
	387(L) x 237(W) x 495(H)	96V	24	4	3522	3648	755
		120V	30	4	4396	3648	755
		240V	60	6	5270	5072	755
		360V	90	6	7455	5072	755


STANDARD LAYOUT OF BATTERY BANK WITH MS STILLAGES

Battery Type	Cell Voltage	System Voltage	No. of Stillages	No. of Rows	Dimensions (mm)		
					Length (±5)	Width (±5)	Height (±5)
LMXT900 & LMXT1000	2V	48V	4	2	3164	2750	597
		96V	8	4	3164	4050	597
		120V	8	4	3707	4050	597
		240V	16	8	3707	7950	597
		360V	24	12	3707	11850	597

^{*} These are our standard layouts. Other options can be offered against specific requirement.







Sales and Service of Exide batteries are supported PAN INDIA through its 30 branches, 30 Exide Power Centers, 3500 dealers.



Please address your queries & comments to :

Head Office

Kolkata 'Exide House', 59E Chowringhee Road, Kolkata - 700 020, Phone (033) 2283 2120/33/ 36/50/51/71/ 2238/39, Fax (033) 2283 2632/37

Corporate Marketing Office

6A Hatibagan Road, Entally, Kolkata - 700 014, Phone (033) 2286 6158/6159, Fax (033) 2286 6186, Kolkata

E-mail: indlcare@exide.co.in

Regional Offices

'Exide House', 3E/1 Link Road, Jhandewalan New Delhi

Extension, New Delhi - 110 055,

Phone (011) 2362 7095/96/98, Fax (011) 2355 5703

Chennai Exide Industries Limited, New No. 824/2, Old No. 398, Third Floor, Anna Salai, Nandanam, Chennai - 600 035 (Before Hyundai Showroom), Phone (044) 4907 5100,

(044) 4907 5125, Fax (044) 4907 5126

'RAHEJAS', 5th Floor, 8C Main Avenue, V P Road, Santacruz (West), Mumbai - 400 054, Phone (022) Mumbai 2646 5283/84, Fax (022) 2646 5042

Kolkata

6A Hatibagan Road, Entally, Kolkata - 700 014,

Phone (033) 2284 3137/3168/3169.

Fax (033) 2289 7455

Branch Offices

Ph.: (0671) 2686151 Cuttack Guwahati Ph.: (0361) 245 1669 Jamshedpur Ph.: (0657) 229 3022/0785,

Fax (0657) 229 0894 (PP)

Patna Ph.: (0612) 322 3865, Fax (0612) 252 9902 (PP) Ph.: (0353) 253 8321, Fax (0353) 252 3731 Siliguri

Chandigarh Ph.: (0172) 500 0014 Dehradun Ph.: (0135) 324 7766

Ghaziabad Ph.: (0120) 437 7031

Ph.: (0141) 519 1206, Fax (0141) 519 1221 Jaipur Jalandhar Ph.: (0181) 500 9305/9315/9321/9322,

Fax (0181) 500 9326

www.exide4u.com Toll Free No. 1800-103-5454

Lucknow Ph.: (0522) 404 1896/1899/491 3709

Ph.: (0542) 220 2129 Varanasi

Ph.: (080) 4128 3793, Fax (080) 2574 4226 Bengaluru

Coimbatore Ph.: (0422) 222 1846 / 222 1408, Fax (0422) 222 0858

Ph.: (040) 6516 3958 Hyderabad

Ph.: (0484) 414 9351, 414 9352, Fax (0484) 414 9311 Kochi

Ahmedabad Ph.: (079) 6510 8207, Fax (079) 2963 0532

Ph.: (0731) 654 2293

Mumbai (Fort) Ph.: (022) 2207 2188/89, Fax (022) 2207 8631

Ph.: (0712) 253 9972/9973, Nagpur

Fax (0712) 253 8348

Pune Ph.: (020) 3230 4041-45, Fax (020) 2443 0094

Vadodara Telefax: (0265) 235 4240